


Henry Gallacher Ltd

PARA RUBBER / SHOTBLAST RUBBER DATA SHEET



Henry Gallacher

Limited

Grade	No6	
Colour	TAN	
Elastomer	NR/SBR	
Quality	PREMIUM SHOTBLAST	
Hardness Shore A ±5	45°	ISO 7619-1
SG (g/cm²)	1.05	ISO 2781
Tensile (N/mm²)	16	ISO 37
Elongation %	600	ISO 37
Compression %	30	ISO 815-1
Tear Strength	25	ISO 34-1
Abrasion mm³	85	ISO 4649
Temperature (°C) from	-40	
Temperature (°C) to	85	

Roll Tolerances

Width tolerance:	+/- 2%	ISO 3302 SW1
Length tolerance:	+/- 2%	ISO 3302 SW1

Thicknesses available

1mm to 6mm	1.4m x10m
8mm to 25mm	1.4m x 5m

Thickness

0.5– 1mm	+/- 0.2mm
1.5mm –3mm	+/- 0.3mm
4mm—5mm	+/- 0.4mm
6mm	+/- 0.5mm
8mm	+/- 0.7mm
10mm—15mm	+/- 1mm
20mm	+/- 1.4mm
25mm	+/- 1.75mm

Items listed above usually ex stock.



Henry Gallacher

Limited

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.
Advice is available but final responsibility remains with the customer.