

PRODUCT DATASHEET

FLEXICARB® RGS 4



RGS 4 is a high purity graphite laminate reinforced with a stainless steel core.

Service:

FLEXICARB® RGS 4 can be used to seal a wide range of media at moderate combinations of temperature and pressure. The product is not recommended for sealing against strong chemical or oxidising agents.

Maximum recommended temperature:

Thermal oxidising media 370°C
Inert or reducing media 700°C

For applications sealing inert or reducing media, at temperatures in excess of 370°C, attention must be given to the possibility of oxidative attack on the gasket from the external environment.

For long term continuous use in oxidising environments at temperatures in excess of 370°C please consult Flexitallic Applications Engineering Department.

Maximum recommended pressure:

ASME B16.5 Class rating pressure systems up to and including 600.

PN rated pressure systems up to and including PN100.

Materials:

Facing material:
98% pure graphite foil.

Reinforcement:

0.05mm thick flat stainless steel UNS S31600

Bond Type:

Adhesive.

Availability:

Sheet size:
1.0m x 1.0m
1.5m x 1.5m

Thickness range:

0.75mm to 3.0mm

Colour: Silver / Grey

Typical Physical Properties:

Thickness	1.5mm
Density	1.2gcm ⁻³
ASTM F36A Compressibility	40%
ASTM F36A Recovery	20%
BS 7531 Residual Stress	32MPa
ASTM F152 Tensile Strength	20MPa
Leachable Chloride Ion Content	< 50ppm
Leachable Fluoride Ion Content	< 50ppm

This Data Sheet refers to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the Company in relation to same.

We reserve the right to change the details given on this Data Sheet as additional information is acquired. Customers requiring the latest version of this Data Sheet should contact our Applications Engineering Department.

The information given and, in particular, any parameters, should be used for guidance purposes only. The Company does not give any warranty that the product will be suitable for the use intended by the customer.

Health & Safety

For further Health and Safety information please see the relevant Material Safety Datasheets or contact Flexitallic UK Ltd.