



Henry Gallacher

Limited

Viton™ Rubber Sheeting

Colour: Black

66% Fluorine Content

Very good resistance to:

- Weathering
- Ozone
- Chemical media
- Oil and Gasoline
- Heat

PROPERTY	RESULT	TEST METHOD
Elastomer	Dipolymer	
Hardness	70° (±5°) Shore A	GB/T 531.1-2008
Density	1.9 ± 0.1 g/cm ³	GB/T 533-2008
Tensile Strength	≥ 11MPa	GB/T 528-2009
Elongation at Break	210 ± 30%	GB/T 528-2009
Compression Set after 22 hrs @ 200°C	≤ 35%	
Temperature Resistance	-13°C to + 230°C Continuous up to 250°C Intermittent	

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.